

RAPID 6000

Technical Data Sheet

PROPERTIES	VALUE
Pot Life @ 77°F (25°C) (ASTM 2196)	3 hours
Dry Time @ 77°F (25°C), 55% R.H.	
To Touch	2 - 4 hours
To Handle	4 - 6 hours
To Recoat	6 - 8 hours
Solids by Weight	71% - 73%
Solids by Volume	62% - 65%
Recommended Dry Film Thickness	3 to 5 mils (75 - 125 microns) per coat
Viscosity @ 77°F (25°C)	80 KU (mixed)
Theoretical Coverage	994 ft ² /gallon @ 1 mil DFT (92,35 m ² /L @ 25,4 microns DFT)
Film Thickness	
Wet	5.0 - 8.0 mils (125 - 203 microns) per coat
Dry	3.0 - 5.0 mils (76 - 125 microns) per coat
Mixing Ratio	4:1
Atmospheric Temperature Limit	200°F (93°C)
Flash Point	40°F (4°C) TCC
VOC's	2.5 lbs/gal (300 gr/l)
Color	white

STORAGE AND HANDLING:

Store the containers in a dry, well ventilated area.
The containers should be kept tightly sealed.
Shelf life: 2 years.
DOT classification: Paint UN 1263

PACKAGING:

1 gallon kits 5 gallon kits
(3.8 liter kit) (19 liter kit)
Special kit sizes are available.

HEALTH AND SAFETY:

Spray or brush under well ventilated conditions.
Wear suitable protective clothing and glasses.
See safety data sheet.